



# Sani-Pro<sup>®</sup> HpHT HFK ULTRAFILTRATION ELEMENTS

## Sanitary Ultrafiltration Spiral Elements with High pH and Temperature Cleaning

### PRODUCT DESCRIPTION

**Membrane Chemistry:** Proprietary semi-permeable polyethersulfone (PES)  
**Membrane Type:** HpHT HFK-131 with Molecular Weight Cutoff (MWCO) of 10,000 Daltons  
 HpHT HFK-328 with Molecular Weight Cutoff (MWCO) of 5,000 Daltons  
**Construction:** Sanitary spiral wound element with controlled net outer wrap  
**Regulatory Status:** Compliant with US FDA CFR Title 21, EC Reg. No. 1935/2004, and EU Reg. No. 10/2011. Halal-certified by the Islamic Food and Nutrition Council of America (IFANCA).  
**Options:** Diameter: 6.3", 6.4", or 8.0"  
 Outer Wrap: Controlled or trimmable  
 Feed Spacer: 30 mil, 45 mil, 62 mil or 80 mil

### NOMINAL SPECIFICATIONS

Model	Membrane Area*							
	30-mil Spacer		45-mil Spacer		62-mil Spacer		80-mil Spacer	
	ft <sup>2</sup>	(m <sup>2</sup> )						
HpHT 3838 K131	71	(6.6)	58	(5.4)	-	-	-	-
HpHT 4336 K131	-	-	80	(7.4)	-	-	-	-
HpHT 6438 K328/K131	216	(20.0)	180	(16.7)	137	(12.7)	112	(10.4)
HpHT 8038 K328/K131	350	(32.5)	283	(26.3)	228	(21.2)	-	-


\* - not all options available

### OPERATING AND DESIGN INFORMATION\*

**Typical Operating Pressure:** 30 - 120 psi (2.1 - 8.3 bar)  
**Maximum Operating Pressure:** 140 psi (9.7 bar)  
**Operating Temperature Range:** 41 - 140°F (5 - 60°C)  
**Cleaning Temperature Range:** 105 - 185°F (40 - 85°C)  
**Allowable pH - Continuous Operation:** 2.0 - 10.0  
**Allowable pH - Clean-In-Place (CIP):** 1.8 - 12.5  
**Design Pressure Drop Per Element:** 30 mil: 12-16 psi (0.8-1.1 bar)  
 45 mil: 15-20 psi (1.0-1.4 bar)  
 62 and 80 mil: 15-25 psi (1.0-1.7 bar)  
**Design Pressure Drop Per Vessel (3 in series):** 30 mil: 36-45 psi (2.5-3.1 bar)  
 45 mil: 45-60 psi (3.1-4.1 bar)  
 62 and 80 mil: 45-75 psi (3.1-5.2 bar)  
**Design Pressure Drop Per Vessel (4 in series):** 30 mil: 48-60 psi (3.3-4.1 bar)  
 45 mil: 60-68 psi (4.1-4.7 bar)  
**Maximum Pressure Drop above 140°F (60°F):** 15 psi (1.0 bar) between 60-69°C (140-157°F)  
 13 psi (0.9 bar) between 70-79°C (158-175°F)  
 10 psi (0.7 bar) between 80-85°C (176-185°F)

\* Consult KMS Process Technology Group for specific applications.

### NOMINAL DIMENSIONS



Model	A		B		C	
	inches	(mm)	inches	(mm)	inches	(mm)
3838	38.0	(965)	3.8	(96)	0.831	(21.1)
4336	35.5	(902)	4.3	(109)	0.831	(21.1)
6438	38.0	(965)	6.4	(162)	1.138	(28.9)
8038	38.0	(965)	7.9	(201)	1.138	(28.9)

## Sani-Pro® HpHT HFK ULTRAFILTRATION ELEMENTS

---

### Membrane Characteristics:

- The membrane used in the Sani-Pro UF elements consists of a semipermeable polyethersulfone (PES) layer on a polyolefin backing material.

### Operating Limits:

- **Operating Pressure:** Maximum operating pressure is listed on the first page of this document. Actual operating pressure is dependent upon system flux rate (application specific) as well as feed, concentration and temperature conditions.
- **Permeate Pressure:** Permeate pressure should not exceed baseline (concentrate) pressure at any time (including on-line, off-line and during transition). Reverse pressure will damage the membrane.
- **Differential Pressure:** The maximum differential pressures per element are listed on the front of this document, including design values for multi-element housings.
- **Temperature:** Maximum operating and cleaning temperatures for the HpHT elements are shown on the first page of this document. Above 60°C (140°F) temperature change should not exceed 5°C (9°F) per minute.
- **pH:** Allowable range for continuous operation and cleaning is shown on the first page of this document.

### Water Quality for Cleaning & Diafiltration:

- **Turbidity and SDI:** Maximum feed turbidity is 1 NTU. Maximum feed SDI is 5.0 (15-minute test).
- **Guidelines:** Please refer to the KMS “Water Quality Guidelines for CIP and Diafiltration” for more detailed information.

### Chlorine and Chemical Exposure:

- Adherence to cleaning and sanitizing procedures including chemical concentrations, pH, temperature, and exposure time is necessary to achieve maximum useful element life. Accurate records must be maintained.
- KMS standard cleaning procedures for the specific applications should be followed. Recommended chlorine exposure time at the defined conditions is 30 minutes per day.
- Residual chlorine concentration during cleaning cycle (CIP) should be 150 ppm @ pH 10.5-11.0. Chlorine concentration should never exceed 200 ppm.

- Chlorine should only be added to the cleaning solution after the pH has been adjusted to 10.5-11.0.
- Iron or other catalyzing metals in the presence of free chlorine or hydrogen peroxide will accelerate membrane degradation.
- Sanitizing should be done only after a complete cleaning cycle and with water of acceptable quality. Refer to cleaning instructions and feedwater quality technical bulletins.

### Cationic Polymers and Surfactants:

Sani-Pro UF membranes may be irreversibly fouled if exposed to cationic (positively charged) polymers or surfactants. Exposure to these chemicals during operation or cleaning is not recommended and will void the warranty.

### Lubricants:

For element installation, use only water or glycerin to lubricate seals. The use of petroleum or vegetable-based oils or solvents may damage the element and will void the warranty.

### Supplemental Technical Bulletins:

- UF Element Cleaning Procedures
- Water Quality Guidelines for CIP and Diafiltration
- HpHT Element Cleaning Procedures

### KMS ASSIST® Service and Ongoing Technical Support:

KMS has an experienced staff of professionals available to assist end-users and OEM's for optimization of existing systems and support for the development of new applications. KMS also offers a complete line of KOCHKLEEN® membrane pretreatment, cleaning, and maintenance chemicals.

### KMS Capability

KMS is the leader in crossflow membrane technology, manufacturing reverse osmosis, nanofiltration, microfiltration, and ultrafiltration membranes and membrane systems. The industries we serve include food, dairy and beverage, semiconductors, automotive, water and wastewater, chemical and general manufacturing. KMS adds value by providing top quality membrane products and by sharing our experience in the design and supply of thousands of crossflow membrane systems worldwide.

*The information contained in this publication is believed to be accurate and reliable, but is not to be construed as implying any warranty or guarantee of performance. We assume no responsibility, obligation or liability for results obtained or damages incurred through the application of the information contained herein. Refer to Standard Terms and Conditions of Sale and Performance Warranty documentation for additional information.*

---

Koch Membrane Systems, Inc., [www.kochmembrane.com](http://www.kochmembrane.com)

Corporate Headquarters: 850 Main Street, Wilmington, Massachusetts 01887-3388 USA. Tel.: 1-888-677-KOCH.

For related trademark information, visit [www.kochmembrane.com/legal](http://www.kochmembrane.com/legal)

Koch Membrane Systems, Inc. is a Koch Chemical Technology Group, LLC company.

© 2019 Koch Membrane Systems, Inc. All rights reserved worldwide.

01/19 Rev 19-1